








TEKNISKE DATA	Egenskaper	Norm	Enhet	Screed Eco <sup>PRO</sup>
<p><b>Screed Eco</b>  </p> <p>Gummi gulvbelegg. Betong med slett overflate.</p> <p>Leveres i rull og flis.</p>     <p><b>POLYFLOR</b>™ COVERING THE WORLD</p> <p><b>Polyflor Nordic</b> Kjelsåsveien 168 B 0884 OSLO Tel.: 23 00 84 00 Fax: 23 00 84 10 <a href="mailto:firmapost@polyflor.no">firmapost@polyflor.no</a> <a href="http://www.polyflor.no">www.polyflor.no</a></p>	Type	EN 1817		
	Overflate			
	Mønster			Betong
	Farger			6
	Totalvekt	EN 430	g/m <sup>2</sup>	4.900
	Klassifisering	EN 685		23, 34, 43
	Totaltykkelse	EN 428	mm	3,0
	Format rull	EN 426	m / m <sup>2</sup>	1,9 x 10 / 19 m <sup>2</sup>
	Format fliser	EN 427	mm / m <sup>2</sup>	61 x 61cm / 5,95 m <sup>2</sup>
	Restinntrykk	EN/ISO 24343-1 (EN 433)	mm	0,08
	Slitasjetest	ISO 4649 Met.A-5N	mm <sup>3</sup>	165
	Dimensjonsstabilitet	EN/ISO 23999 (EN 434)	%	± 0,30
	Brann	EN 13501-1		C <sub>fl</sub> -sl
	Friksjon	DIN 51130		R9
	Trinnlyd	ISO 10140-3	dB	9
	Hardhet	ISO 7619 shore A		88
	Elektrisk oppladning	EN 1815	kV	≤ 2 (antistatisk)
	El. Motstand	EN 1081 Met.A	Ohm	>10 <sup>10</sup>
	Kjemikaliebestandighet	EN/ISO 26987 (EN 423)		ja*
	Trinsestol	EN 425		Ja (W-hjul)
Varmekabler			ja, ikke over 27°C	
*Motstandsdyktig. Ved lengre tids påvirkning eventuelt høy konsentrasjon, vennligst ta kontakt				