

TEKNISKE DATA


Egenskaper

Norm

Enhet


Kayar / LL ^{PRO}

Kayar / LL 


Artigo Kayar / LL – 

Fliser for løst legging. Slett overflate med kokosfiber.

Leveres i flis



Polyflor Nordic
Kjelsåsveien 168 B
0884 OSLO
Tel.: 23 00 84 00
Fax: 23 00 84 10
firmapost@polyflor.no
www.polyflor.no

Type	EN 1817		
Overflate			
Mønster			Kokosfiber
Farger			4
Totalvekt	EN 430	g/m ²	8.600
Klassifisering	EN 685		23, 34, 43
Totaltykkelse	EN 428	mm	5,0
Format rull	EN 426	m / m ²	-
Format fliser	EN 427	mm / m ²	61 x 61 cm / 3,72 m ²
Restinntrykk	EN 433	mm	≤ 0,20
Slitasjetest	ISO 4649 Met.A-5N	mm ³	190
Dimensjonsstabilitet	EN 434	%	± 0,30
Brann	EN 13501-1		B _{f1} - sl
Friksjon	DIN 51130		≥ 6 (R9)
Trinnlyd	ISO 140 - 8	dB	16
Hardhet	ISO 7619 ≥ 75 shore A		85 ± 5
Elektrisk oppladning	EN 1815	kV	≤ 2 (antistatisk)
Ei. Motstand	IEC 60093	Ohm	>10 ¹⁰
Kjemikaliebestandighet	EN 423		ja*
Rullestol	EN 425		Ja, W-hjul
Varmekabler			-

*Motstandsdyktig. Ved lengre tids påvirkning eventuelt høy konsentrasjon, vennligst ta kontakt